



SC10 SOLVENT CLEAR

SOLVENT BASED CLEAR PLOYMER COATING AND CONCRETE SEALER.



USES

- Filling roof cracks by pouring in or seeping in.
- Deep sealing of porous, chalky or powdery cements surfaces before painting.
- It resists blistering in stagnant water on the rooftop and the alkalinity of the cement.
- Sealing and glazing of roof tiles, so to preserve and to prevent black mildew growth and staining.
- Sealing of fine gap of aluminium window frame.
- Car Park cement floor gloss sealing coat to prevent water ingress, reduce staining, dust proofing.

APPLICATION METHOD

- Surface to be coated has to be clean and dry for maximum absorption. It is better to seal the surface with **W 4 WATER REPELLENT** for better paint bonding and durability.
- **SC 10** can be diluted **1 : 2 with Thinner**, (Toluene - slow drying or Xylene - fast drying) for sealing of porous concrete.
- **SC 10** is to be used undiluted for pouring into concrete cracks for deep sealing and penetration.

CAUTION

- Not suitable for coating over Red Brick's wall, due to moisture being trapped has no escape passage, resulting in blistering and white patchy coating.
- **W 4 WATER REPELLENT** is vapour permeable and is most suitable for the job.
- **Flammable Solvent product, use in ventilated area, avoid naked flame.**
- **Allow spent paint in the tin to dry up before disposal, to avoid polluting the waterways.**
- **The coated surface will be very slippery. Avoid Slip & Fall.**

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 / 6364 5060 / 6367 3676 Fax: (65) 6364 0629

war99@singnet.com.sg www.warrior.com.sg





SC10 SOLVENT CLEAR

SOLVENT BASED CLEAR PLOYMER COATING AND CONCRETE SEALER.

TECHNICAL DATA

- Physical Form: Clear solution.
- Solvent used: Toluene: Slow drying;
Xylene: Fast drying.
- Elongation: 100 % of Coating Thickness
- UV resistance: Excellent, Non-yellowing.
- Weathering property: Excellent.
- Water seeping test: Excellent. 5% water seeps through over 24 hours (Water cup test).
- Stagnant water test: Excellent. No change in physical property.
- Ignition Temperature: 40 °C open flame when wet. 100 °C open flame when dry.
- Drying time: Surface dry (15 minutes at 25 °C).
Fully cured (8 hours). °
- Coverage: 1 kg will cover 200 sq. feet or 20 sq. metre.

PACKING

1 litre-tin / 5 litre-tin / 20 litre-tin

Disclaimer: The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 / 6364 5060 / 6367 3676 Fax: (65) 6364 0629

war99@singnet.com.sg www.warrior.com.sg

